

# SHINPET 5015W

## TECHNICAL SPECIFICATION

Lot No.: I57/69801

PROPERTY	UNIT	VALUE	TEST METHOD
I.V.	d l / g	0.80 ± 0.02	ASTM D-2857
H <sub>2</sub> O CONTENT	wt %	< 0.5	ASTM D-4019
MELTING POINT	° C	246 ± 4	ASTM D-3418
COLOR ( b )		0.0 ± 2.0	JIS Z 8722
PELLET SHAPE		OVAL	
BULK DENSITY	g / cm <sup>3</sup>	0.9 ± 0.1	
PACKING	Kg / BAG	1100	
A.A. CONTENT	ppm	< 1.0	CELANESE

- **NOTE: RECOMMENED DRYING TEMPERATURE/TIME**  
160 ~ 170 °C / 5 ~ 7 hours

Properties reported here are typical of average lots. Makes no representation that the material in any particular shipment will conform exactly to the values given. Neither Polyindex nor its marketing affiliates shall be responsible for the use of this information, or of any product, method, or apparatus mentioned. User makes their own determination of suitability and completeness for their own use, for the protection of the environment, and for the health and safety of user's employees and purchaser of user's products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the seller's conditions of sales.